



# EMSL Analytical, Inc.

4140 Litt Drive Hillside, IL 60162  
Tel/Fax: (773) 313-0099 / (773) 313-0139  
<http://www.EMSL.com> / [chicagolab@emsl.com](mailto:chicagolab@emsl.com)

**EMSL Order:** 262500819  
**Customer ID:** DEIG62  
**Customer PO:**  
**Project ID:**


**Attention:** Gary Deigan  
Deigan & Associates, LLC  
28835 N. Herky Drive  
Unit 120  
Lake Bluff, IL 60048  
**Project:** ALERG FIBERGLASS

**Phone:** (847) 623-9356  
**Fax:** (847) 578-5010  
**Received Date:** 01/27/2025 10:10 AM  
**Analysis Date:** 01/30/2025  
**Collected Date:**

## Test Report: Asbestos Analysis of Bulk Materials via AHERA Method 40CFR 763 Subpart E Appendix E supplemented with EPA 600/R-93/116 using Polarized Light Microscopy

Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
001FG <small>262500819-0001</small>	INSULATION	Yellow Fibrous Homogeneous	98% Glass	2% Non-fibrous (Other)	None Detected
002FG <small>262500819-0002</small>	INSULATION	Yellow Fibrous Homogeneous	98% Glass	2% Non-fibrous (Other)	None Detected
003FG <small>262500819-0003</small>	INSULATION	Yellow Fibrous Homogeneous	98% Glass	2% Non-fibrous (Other)	None Detected

Analyst(s)  
Mazen Elkhatib (3)

  
James Hahn, Laboratory Manager  
or Other Approved Signatory

EMSL maintains liability limited to cost of analysis. Interpretation and use of test results are the responsibility of the client. This report relates only to the samples reported above, and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. The report reflects the samples as received. Results are generated from the field sampling data (sampling volumes and areas, locations, etc.) provided by the client on the Chain of Custody. Samples are within quality control criteria and met method specifications unless otherwise noted. The above analyses were performed in general compliance with Appendix E to Subpart E of 40 CFR (previously EPA 600/M4-82-020 "Interim Method") but augmented with procedures outlined in the 1993 ("final") version of the method. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. Non-friable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Estimation of uncertainty is available on request.

Samples analyzed by EMSL Analytical, Inc. Hillside, IL NVLAP Lab Code 200399-0

Initial report from: 01/30/2025 15:20:30